

P61516 | PANTONE® VIBRANT by Felix Schoeller

Flat Matt 230

MICROPOROUS RESIN-COATED PAPER

PANTONE® VIBRANT.

by Felix Schoeller

PRODUCT SPECIFICATION *

Weight	g/m ²	232	± 6
Thickness	µm	230	± 6
	mil	9.0	± 0.2
Gloss BYK (60°)		20	± 0
Colour Elrepho UVO (D65)	L	96,1	±
	a	-0,6	±
	b	0,0	±
	delta b	9,1	±
i1 Pro2	L*M0	97,0	
	a*M0	0,7	
	b*M0	-5,8	
	L*M1	97,2	
	a*M1	1,0	
	b*M1	-8,2	
CIE whiteness (D65/10°)		> 130	
Opacity	%	> 92	

Printability

Simplex printable

Printing Technology

💧 Inkjet water-based

Compatibility

Can be used on all commercial thermal, piezo water-based printing systems like Epson, Canon, Hewlett-Packard, Kodak, Encad etc.

Available on request



FSC® C020254

PEFC®

KEY APPLICATIONS

Proof & Prepress

- Prints for colour communication, e.g. packaging, fashion, marketing collaterals

BENEFITS & PROPERTIES

- Matching of 99.71% of all PANTONE® colours possible (The results of matching 99.71% of the PANTONE FORMULA GUIDE solid coated palette, is based on printing with an Epson Stylus Pro 4900, on PANTONE® VIBRANT by Felix Schoeller and without any special colour management systems.)
- Easy-to-use
- Reproducibility by outstanding media colour consistency
- Surface as offset papers
- Instant dry
- Produced under License Agreement with Pantone LLC. PANTONE is a trademark of Pantone LLC in the United States and/or other countries.

Directions for use

Store material only in original packaging under normal climatic conditions (23°C, 50 % RH). Protect material from direct sunlight. It is recommended to adapt the material to indoor climate at least 24 hours before usage.

* Modifications reserved.

Version 05/2016